



Evaluation Listing CCMC 13683-L Icynene ProSeal™ (MD-C-200v3)

MasterFormat:	07 21 19.02
Evaluation issued:	2014-04-16
Revised:	2018-03-27
Re-evaluation due:	2017-04-16
Re-evaluation in progress	

1. Evaluation

This product conforms to CAN/ULC-S705.1-01 (with Amendments No. 1, 2 and 3), Type 2.

For retrofit constructions, time before occupancy is one (1 day).

The LTTR for 50 mm is RSI 2.02.

2. Description

The product is a Type 2, spray-applied rigid polyurethane foam of medium density. The foam system consists of two components: “Icynene Base Seal[®]” isocyanate and a polyurethane resin identified as “Icynene ProSeal™ (MD-C-200v3).” The two components are mixed on-site by a qualified installer with fixed-ratio positive displacement equipment.

The colour of the final cured product is platinum.

3. Standard and Regulatory Information

See the Annex, appended to this Listing, which summarizes the product standard.

This/these product(s) was/were evaluated to the product standard referenced in the Annex current as of 2011-04-13. Note that the Annex may have been updated since this Listing was issued to include more recent editions of the applicable product standard. Therefore this Listing may not reflect the requirements contained in any updated version of this product standard.

3.1 Qualified Installers

This is a site-manufactured product whereby Icynene Inc. requires that only specific qualified installers be authorized to install their proprietary spray polyurethane insulation in buildings. In accordance with the Icynene Inc. site quality assurance program (SQAP), the certification organization (CO) Caliber Quality Solutions Inc. (Caliber) has been commissioned to license the specified installers and issue them the requisite identification card. All specified installers must have their Caliber identification card.

3.2 Third-party Field Auditing of Qualified Installers

Icynene Inc., as part of their SQAP, also stipulates site audit inspections be conducted by site inspectors licensed by Caliber. Upon completion of the site audit of the specified installers, Caliber will report the product's conformity results and any corrective action required, if necessary, to Icynene Inc. Building officials who would like site-audit inspections to be conducted on specific building sites can contact Caliber at:

Caliber Quality Solutions Inc., delivering Morrison Hershfield QAP
Suite 1000, 120 Eglinton Ave. East
Toronto, ON M4P 1E2

Telephone: 888-572-7435

Listing Holder

Icynene Inc.
6747 Campobello Road
Mississauga, ON L5N 2L7

Telephone: 877-636-2648

Email: inquiry@icynene.com

Web site: www.icynene.com

Site – Finished Product

The foam insulation is a site-manufactured product.

Plant – Raw Materials

Mississauga, ON

Disclaimer

This Listing is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.

Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to http://www.nrc-cnrc.gc.ca/eng/solutions/advisory/ccmc_index.html, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone: 613-993-6189. Fax: 613-952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified:
2018-03-27



Spray-Applied Rigid Polyurethane Foam Insulation, Medium Density [Annex]

MASTERFORMAT: 07 21 19.02

Issued: 2011-04-13

Scope

These Evaluation Listings apply to spray-applied rigid polyurethane foam, medium density, intended for use as thermal insulation for both building and non-building applications, whether applied on a building site or in a prefabrication (manufacturing) process. This material is also known as foamed in-situ insulation. The continuous-use temperature is within the range -60°C to $+80^{\circ}\text{C}$.

The proponent has demonstrated that the product meets the following standard (see Table 1 for the performance requirements):

- CAN/ULC-S705.1-01 (including Amendments 1 and 2), “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification”; or
- CAN/ULC-S705.1-01 (including Amendments 1, 2 and 3), “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification.”

Spray-applied rigid polyurethane foam, medium density, must be installed by a licensed installer in accordance with the manufacturer’s instructions and the following standard:

- CAN/ULC-S705.2-05, “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Application.”

For compliance to CAN/ULC-S705.2, users should contact the third-party organization that has been identified by the foam manufacturer as the third party operating the field quality assurance program (FQAP) for the foam product (see product listing).

Standard

Table 1. Technical Requirements for Physical Properties

Property	Unit	Requirement	
		Minimum	Maximum
Air permeance (mandatory material testing)	L/s @ 75 Pa	No min.	0.02
Air permeance (optional system testing)	L/s @ 75 Pa	No min.	0.05
Apparent core density	kg/m ³	28	No max.
Compressive strength	kPa	170	No max.
Dimensional stability volume change at:	-20°C	%	No min. -1
	80°C	%	-1 8
	70°C, 97 ± 3% RH	%	No min. 14
Surface burning characteristics – flame spread	–	No min.	500 ¹
Open-cell content volume	%	No min.	8
Initial thermal resistance of a 50-mm-thick specimen after 3 days at 23 ± 2°C	m ² ·°C/W	2.5	No max.
Conditioned thermal resistance of a 50-mm-thick specimen after:	180 days at 23 ± 2°C, or	m ² ·°C/W	Declare ² No max.
	90 days at 60 ± 2°C		
Long-term thermal resistance of a 50-mm-thick specimen – Type 1	m ² ·°C/W	1.8	No max.
Long-term thermal resistance of a 50-mm-thick specimen – Type 2	m ² ·°C/W	2.0	No max.
Tensile strength	kPa	200	No max.
Volatile organic emissions	–	Pass ³	No max.
Water absorption by volume	%	No min.	4
Water vapour permeance of a 50-mm-thick specimen	ng/(Pa·s·m ²)	No min.	60

Notes to Table 1:

- ¹ Results are valid for qualification to the standard. As noted in the standard, “for building code purposes, the flame-spread rating shall be conducted in accordance with the code-specified flame-spread test details with respect to the number of specimens to be tested, specimens tested intact and cut specimens.”
- ² This requirement is only referenced in CAN/ULC-S705.1-01 (with Amendments 1 and 2).
- ³ “Pass” means that after 30 days the volatile compound emissions do not exceed the maximum indoor air concentration stated in Table 2 of CAN/ULC-S705.1. In cases of retrofit construction (e.g., occupied buildings), CAN/ULC-S705.2 requires that the ventilation rate be no less than 0.3 air changes per hour within the working area during the application of the product and that the working area be isolated during spraying. The same ventilation rate is required after the product has been sprayed and for the time period determined in accordance with CAN/ULC-S705.1. See the product listing for the time period required before occupancy.

Labelling

In compliance with CAN/ULC-S705.1-01 (with Amendments 1 and 2), each liquid component container must be identified as either the polyisocyanate component (“A”) or the resin component (“B”). Unless otherwise specified, each container must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number;
- date of manufacture;
- “use before” date;
- the means to identify the installed product; and
- the phrase “CAN/ULC-S705.1” indicating conformance to the standard.

In compliance with CAN/ULC-S705.1-01 (with Amendments 1, 2 and 3), each liquid component container must be identified as either the polymeric isocyanate component (“A”) or the resin component (“B”). The polymeric isocyanate component must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number; and
- date of manufacture.

The resin component must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number;
- date of manufacture;
- “use before” date;
- the means to identify the installed product;
- the phrase “CAN/ULC-S705.1” indicating conformance to the standard; and
- LTTR (50 mm) RSI result.

National Building Code of Canada (NBC)

NBC References

CAN/ULC-S705.1-01 is referenced in Table 5.10.1.1. and Clause 9.25.2.2.(1)(g) of Division B of the NBC 2010.

CAN/ULC-S705.2-05 is referenced in Sentence 5.3.1.3.(3), Table 5.10.1.1., and Sentence 9.25.2.5.(1) of Division B of the NBC 2010.